

Outgassing Data Properties As per ASTM E595

| Isola Product | Total Mass Loss (TML) % | Collected Volatile Condensable Material (CVCM)% | Water Vapor Recovered (WVR)% |
|---------------|-------------------------|---|------------------------------|
| 185HR | 0.36 | 0.01 | 0.25 |
| 254 | 0.12 | 0.01 | 0.06 |
| 370 Turbo | 0.32 | 0.01 | 0.06 |
| 370HR | 0.22 | 0.01 | 0.07 |
| Astra® MT77 | 0.15 | <0.01 | 0.09 |
| DE104 | 0.21 | 0.01 | 0.07 |
| FR406 | 0.27 | 0.00 | 0.10 |
| FR406N | 0.52 | 0.01 | 0.16 |
| FR408 | 0.13 | 0.01 | 0.07 |
| FR408HR | 0.11 | 0.01 | 0.12 |
| IS410 | 0.49 | 0.01 | 0.22 |
| G200 | 0.21 | 0.00 | 0.12 |
| IS400 | 0.21 | 0.01 | 0.07 |
| IS415 | 0.10 | 0.01 | 0.10 |
| IS550H | 0.37 | 0.01 | 0.14 |
| IS620i | 0.18 | 0.01 | 0.10 |
| IS680 | 0.19 | 0.01 | 0.07 |
| I-Speed® | 0.12 | 0.01 | 0.09 |
| I-Tera® MT40 | 0.15 | <0.01 | 0.08 |
| P95 (HB) | 0.88 | 0.02 | 0.36 |
| P96 (V-0) | 0.77 | 0.01 | 0.78 |
| Tachyon 100G | 0.14 | <0.01 | 0.07 |
| TerraGreen | 0.13 | <0.01 | 0.07 |

Test Method: The Outgas Test was performed in a vacuum environment of less than 5×10^{-5} torr according to ASTM E595, for a duration of 24 hours, at 125°C. The TML, CVCM, and the WVR were measured after the test. The following table lists the results of the analysis.