

Dielectric Constant(Dk) / Dissipation factor (Df) Table

Core Data

Thickness (inch)	Thickness (mm)	Dielectric Constant (DK)/ Dissipation Factor (DF)				
		2 GHz	5 GHz	10 GHz	15 GHz	20 GHz
0.010	0.254	3.38	3.38	3.38	3.38	3.38
0.030	0.762	3.38	3.38	3.38	3.38	3.38
0.060	1.524	3.38	3.38	3.38	3.38	3.38
0.0066	0.168	3.45	3.45	3.45	3.45	3.45
0.020	0.508	3.45	3.45	3.45	3.45	3.45
0.060	1.524	3.45	3.45	3.45	3.45	3.45
0.010	0.254	3.45	3.45	3.45	3.45	3.45
0.010	0.254	3.45	3.45	3.45	3.45	3.45
0.020	0.508	3.45	3.45	3.45	3.45	3.45
0.030	0.762	3.45	3.45	3.45	3.45	3.45
		0.0033	0.0033	0.0033	0.0033	0.0033
		0.0033	0.0033	0.0033	0.0033	0.0033

NOTE

Revisions:

A-Original Release - 4/17

B-Added 10 mil 3.60 Dk and 30 mil 3.45 Dk - 2/20

Isola, the Isola logo, Astra, Chronon, GETEK, I-Fill, IsoDesign, IsoStack, I-Speed, I-Tera, Polyclad, Stratus, TerraGreen, and The Base for Innovation are registered trademarks or trademarks of ISOLA USA Corp. in the United States and in other countries.

Copyright © 2021 Isola Group. All rights reserved.