

IPC-4101 /21 /24 /26 /121 /124 /129 UL - File Number E41625

IS410 is a high-performance FR-4 epoxy laminate and prepreg system designed to support the printed circuit board industry's requirements for higher levels of reliability and the trend to use lead-free solder.

### PRODUCT FEATURES

#### Industry Recognition

- UL File Number: E41625
- RoHS Compliant

#### Performance Attributes

- Lead-free assembly compatible
- 6x 288°C solder float capable

#### Processing Advantages

- FR-4 process compatible

### PRODUCT AVAILABILITY

#### Standard Material Offering: Laminate

- 2 to 125 mil (0.05 to 3.2 mm)

#### Copper Foil Type

- HTE Grade 3
- RTF (Reverse Treat Foil)

#### Copper Weight

- ½, 1 and 2 oz (18, 35 and 70 µm) available
- Thinner copper foil available

#### Standard Material Offering: Prepreg

- Tooling of prepreg panels

#### Glass Fabric Availability

- E-glass
- Square weave glass
- Mechanically spread glass

Isola's IS410 has a glass transition temperature (Tg) of 180°C and is specially formulated for superior performance through multiple thermal excursions, passing 6X solder tests at 288°C. IS410 is optimized for enhanced drilling performance allowing high aspect ratio holes of ≤10 mils. Its unique resin chemistry provides CAF resistance with the benefit of long-term reliability of boards built with small feature designs.

### PRODUCT ATTRIBUTES



### TYPICAL MARKET APPLICATIONS



### ORDERING INFORMATION:

Contact your local sales representative or contact [info@isola-group.com](mailto:info@isola-group.com) for further information.

#### Isola Group

6565 West Frye Road Chandler, AZ 85226  
Phone: 480-893-6527  
Fax: 480-893-1409

#### Isola Asia Pacific

(Hong Kong) Ltd. 12/F, Kin Sang Commercial Centre, 49 King Yip Street, Kwun Tong, Kowloon,  
Hong Kong  
Phone: 852-2418-1318  
Fax: 852-2418-1533

#### Isola GmbH

Isola Strasse 2 D-52348 Düren, Germany  
Phone: 49-2421-8080  
Fax: 49-2421-808164

# Typical Values Table

| Property   |  | Typical Value      | Units            |                          | Test Method           |
|--|--|--------------------|------------------|--------------------------|-----------------------|
|  |  |                    | Metric (English) | IPC-TM-650 (or as noted) |                       |
| Glass Transition Temperature (Tg) by DSC               |  | 180                | °C               |                          | 2.4.25C               |
| Decomposition Temperature (Td) by TGA @ 5% weight loss |  | 350                | °C               |                          | 2.4.24.6              |
| Time to Delaminate by TMA (Copper removed)             | A. T260  | 50                 | Minutes          |                          | 2.4.24.1              |
|  | B. T288  | 10                 |                  |                          |                       |
| Z-Axis CTE   | A. Pre-Tg  | 55                 | ppm/°C           |                          | 2.4.24C               |
|  | B. Post-Tg   | 250                | ppm/°C           |                          |                       |
|  | C. 50 to 260°C, (Total Expansion)  | 3.5                | %                |                          |                       |
| X/Y-Axis CTE   | Pre-Tg   | 11                 | ppm/°C           |                          | 2.4.24C               |
| Thermal Conductivity                                   |  | 0.5                | W/m-K            |                          | ASTM E1952            |
| Thermal Stress 10 sec @ 288°C (550.4°F)                | A. Unetched  | Pass               | Pass Visual      |                          | 2.4.13.1              |
|  | B. Etched  |                    |                  |                          |                       |
| Dk, Permittivity                                       | A. @ 100 MHz   | 3.96               | —                |                          | 2.5.5.3               |
|  | B. @ 1 GHz   | 3.90               |                  |                          | 2.5.5.9               |
|  | C. @ 2 GHz   | 3.97               |                  |                          | Bereskin Stripline    |
|  | D. @ 5 GHz   | 3.87               |                  |                          | Bereskin Stripline    |
|  | E. @ 10 GHz  | 3.87               |                  |                          | Bereskin Stripline    |
| Df, Loss Tangent                                       | A. @ 100 MHz   | 0.0149             | —                |                          | 2.5.5.3               |
|  | B. @ 1 GHz   | 0.0189             |                  |                          | 2.5.5.9               |
|  | C. @ 2 GHz   | 0.0200             |                  |                          | Bereskin Stripline    |
|  | D. @ 5 GHz   | 0.0230             |                  |                          | Bereskin Stripline    |
|  | E. @ 10 GHz  | 0.0230             |                  |                          | Bereskin Stripline    |
| Volume Resistivity                                     | A. After moisture resistance   | $8.0 \times 10^8$  | MΩ-cm            |                          | 2.5.17.1              |
|  | B. At elevated temperature   | $3.6 \times 10^8$  |                  |                          |                       |
| Surface Resistivity                                    | A. After moisture resistance   | $8.0 \times 10^6$  | MΩ               |                          | 2.5.17.1              |
|  | B. At elevated temperature   | $4.5 \times 10(8)$ |                  |                          |                       |
| Dielectric Breakdown                                   |  | >50                | kV               |                          | —                     |
| Arc Resistance   |  | 129                | Seconds          |                          | —                     |
| Electric Strength (Laminate & laminated prepreg)       |  | 44 (1100)          | kV/mm (V/mil)    |                          | —                     |
| Comparative Tracking Index (CTI)                       |  | 3 (175-249)        | Class (Volts)    |                          | UL 746A<br>ASTM D3638 |
| Peel Strength  | A. Low profile copper foil and very low profile copper foil all copper foil >17 μm [0.669 mil] | 1.14 (6.5)         | N/mm (lb/inch)   |                          | 2.4.8C                |
|  | B. Standard profile copper   | 1.225 (7.0)        |                  |                          | 2.4.8.2A              |
|  | 1. After thermal stress  | 1.14 (6.5)         |                  |                          | 2.4.8.3               |
|  | 2. At 125°C (257°F)  | 0.90 (5.1)         |                  |                          | 2.4.8.3               |
| Flexural Strength                                      | A. Length direction  | 570 (82.6)         | MPa (kpsi)       |                          | 2.4.4B                |
|  | B. Cross direction   | 458 (66.4)         |                  |                          |                       |
| Tensile Strength                                       | A. Length direction  | 420 (60.9)         | MPa (kpsi)       |                          | ASTM D3039            |
|  | B. Cross direction   | 316 (45.8)         |                  |                          |                       |
| Poisson's Ratio  | A. Length direction  | 0.175              | —                |                          | ASTM D3039            |
|  | B. Cross direction   | 0.143              |                  |                          |                       |
| Moisture Absorption                                    |  | 0.20               | %                |                          | 2.6.2.1A              |
| Flammability (Laminate & laminated prepreg)            |  | V-0                | Rating           |                          | UL 94                 |
| Relative Thermal Index (RTI)                           |  | 130                | °C               |                          | UL 796                |

## NOTES

Visit our site <http://www.isola-group.com> for more details.

Revisions:

A: Initial release - 4/17

B: Corrected units for Flexural and Tensile Strength - 8/18

C: Change MOT to RTI 5/19

Isola, the Isola logo, Astra, Chronon, GETEK, I-Fill, IsoDesign, IsoStack, I-Speed, I-Tera, Polyclad, Stratus, TerraGreen, and The Base for Innovation are registered trademarks or trademarks of ISOLA USA Corp. in the United States and in other countries. Copyright © 2021 Isola Group. All rights reserved.