

## Dielectric Constant(Dk) / Dissipation factor (Df) Table

### Core Data

Thickness (inch)	Thickness (mm)	Dielectric Constant (DK)/ Dissipation Factor (DF)				
		2 GHz	5 GHz	10 GHz	15 GHz	20 GHz
0.010	0.254	3.45 0.0032	3.45 0.0032	3.45 0.0032	3.45 0.0032	3.45 0.0032
0.020	0.508	3.45 0.0032	3.45 0.0032	3.45 0.0032	3.45 0.0032	3.45 0.0032
0.030	0.762	3.45 0.0032	3.45 0.0032	3.45 0.0032	3.45 0.0032	3.45 0.0032
0.006	0.152	3.61 0.0036	3.61 0.0036	3.61 0.0036	3.61 0.0036	3.61 0.0036
0.020	0.508	3.61 0.0036	3.61 0.0036	3.61 0.0036	3.61 0.0036	3.61 0.0036
0.030	0.762	3.61 0.0036	3.61 0.0036	3.61 0.0036	3.61 0.0036	3.61 0.0036
0.010	0.254	3.75 0.0036	3.75 0.0036	3.75 0.0036	3.75 0.0036	3.75 0.0036
0.020	0.508	3.75 0.0036	3.75 0.0036	3.75 0.0036	3.75 0.0036	3.75 0.0036
0.030	0.762	3.75 0.0036	3.75 0.0036	3.75 0.0036	3.75 0.0036	3.75 0.0036

### NOTE

Revisions:

A - Original Release - 4/17

Isola, the Isola logo, Astra, Chronon, GETEK, I-Fill, IsoDesign, IsoStack, I-Speed, I-Tera, Polyclad, Stratus, TerraGreen, and The Base for Innovation are registered trademarks or trademarks of ISOLA USA Corp. in the United States and in other countries.

Copyright © 2021 Isola Group. All rights reserved.