

IPC-4101 /134 UL - File Number E41625

TerraGreen® 400G2 laminate materials are our most advanced ultra-high speed, halogen free extremely-low loss design solution.

PRODUCT FEATURES

Industry Recognition

- UL File Number: E41625
- RoHS Compliant

Performance Attributes

- CAF resistant
- Low moisture absorption
- Halogen free
- 0.8 mm pitch capable
- 6x 260°C reflow capable
- 6x 288°C solder float capable

Processing Advantages

- FR-4 process compatible
- Excellent Fill and Flow
- Multiple lamination cycles
- HDI technology compatible

PRODUCT AVAILABILITY

Standard Material Offering: Laminate

- 2 to 10 mil (0.05 to 0.25 mm)

Copper Foil Type

- HVLP3 (VLP1) ≤1.1 micron Rz JIS

Copper Weight

- ½, 1 oz (18 and 35 µm) available
- Thinner copper foil available

Standard Material Offering: Prepreg

- Tooling of prepreg panels
- Moisture barrier packaging

Glass Fabric Availability

- Very Low Dk glass
- Mechanically spread glass

TerraGreen® 400G2 is our Halogen Free material solution for next generation 5G infrastructure, data center systems, high end computing, wired & wireless communications and AI applications. Our novel resin system, ultra smooth HVLP3(VLP1) copper foil and 2nd generation Ultra Low Dk glass has been engineered for very high data rates of >100 Gb/s with excellent cost for loss performance.

The TerraGreen® 400G2 resin system has proven superior CAF performance on tight pitch testing. CAF performance is enhanced by the resin systems excellent interlaminar and bond line adhesion strength.

TerraGreen® 400G2 is lead free compatible and sequential lamination capable and can be processed utilizing standard PCB equipment and processing steps. TerraGreen® 400G2 meets UL94 V-0.

PRODUCT ATTRIBUTES



HIGH DENSITY INTERCONNECT



HALOGEN FREE



HIGH THERMAL RELIABILITY



HIGH TEMPERATURE



5G APPLICATIONS

TYPICAL MARKET APPLICATIONS



AUTOMOTIVE & TRANSPORTATION



NETWORKING & COMMUNICATIONS



AEROSPACE & DEFENSE



COMPUTING, STORAGE & PERIPHERALS

ORDERING INFORMATION:

Contact your local sales representative or contact info@isola-group.com for further information.

Isola Group

6565 West Frye Road Chandler, AZ 85226 Phone: 480-893-6527 Fax: 480-893-1409

Isola Asia Pacific

(Hong Kong) Ltd.12/F, Kin Sang Commercial Centre, 49 King Yip Street, Kwun Tong, Kowloon, Hong Kong Phone: 852-2418-1318 Fax: 852-2418-1533

Isola GmbH

Isola Strasse 2 D-52348 Düren, Germany Phone: 49-2421-8080 Fax: 49-2421-808164

Typical Values Table

Property	Typical Value	Units		Test Method
		Metric (English)	IPC-TM-650 (or as noted)	
Glass Transition Temperature (Tg) by DSC	200	°C	2.4.25C	
Glass Transition Temperature (Tg) by DMA	215	°C	2.4.24.4	
Glass Transition Temperature (Tg) by TMA	180	°C	2.4.24C	
Decomposition Temperature (Td) by TGA @ 5% weight loss	>380	°C	2.4.24.6	
Time to Delaminate by TMA (Copper removed)	A. T288 B. T288	60+	Minutes 2.4.24.1	
Z-Axis CTE	A. Pre-Tg B. Post-Tg C. 50 to 260°C, (Total Expansion)	37 170 1.8	ppm/°C ppm/°C % 2.4.24C	
X/Y-Axis CTE	12/13	ppm/°C	2.4.24C	
Thermal Conductivity	0.54	W/m·K	ASTM E1952	
Thermal Stress 10 sec @ 288°C (550.4°F)	A. Unetched B. Etched	Pass	Pass Visual 2.4.13.1	
Dk, Permittivity	A. @ 10 GHz B. @ 20 GHz	3.10 3.07	— 2.5.5.5	
Df, Loss Tangent	A. @ 10 GHz B. @ 20 GHz	0.0015	— 2.5.5.5	
Volume Resistivity	C-96/35/90	2.0x10 ⁸	MΩ-cm 2.5.17.1	
Surface Resistivity		2.0x10 ⁷	MΩ 2.5.17.1	
Dielectric Breakdown		70	kV 2.5.6B	
Arc Resistance		180	Seconds 2.5.1B	
Electric Strength (Laminate & laminated prepreg)		67 (1700)	kV/mm (V/mil) 2.5.6.2A	
Comparative Tracking Index (CTI)		2 (250-499)	Class (Volts) UL 746A ASTM D3638	
Peel Strength	A. Low profile and very low profile copper foil B. Low profile and very low profile copper foil ... After thermal stress	0.7 (4.1)	N/mm (lb/inch) 2.4.8C 2.4.8.2A	
Flexural Strength	A. Length direction B. Cross direction	393 (57) 338 (49)	MPa (kpsi) 2.4.4B	
Tensile Strength	A. Length direction B. Cross direction	220 (32) 193 (28)	MPa (kpsi) ASTM D3039	
Young's Modulus	A. Length direction B. Cross direction	14.5 (2100) 13.0 (1900)	GPa(kpsi) ASTM D790-15e2	
Flexural Modulus	A. Lengthwise B. Crosswise	12.1 (1750) 11.7 (1700)	GPa (kpsi) ASTM D790-15e2	
Poisson's Ratio	A. Length direction B. Cross direction	0.17 0.22	— ASTM D3039	
Moisture Absorption		<0.1	% 2.6.2.1A	
Flammability (Laminate & laminated prepreg)		V-0	Rating UL 94	
Relative Thermal Index (RTI)		140	°C UL 746	

NOTES

Notes:

All data is preliminary and subject to change

*** Data was developed using 55% RC rigid laminate**

Revisions:

A: Preliminary Release

B: Corrected units for Youngs Modulus from MPa to GPa - 1/24

Isola, the Isola logo, Astra, Chronon, GETEK, I-Fill, IsoDesign, IsoStack, I-Speed, I-Tera, Polyclad, Stratus, TerraGreen, and The Base for Innovation are registered trademarks or trademarks of ISOLA USA Corp. in the United States and in other countries. Copyright © 2021 Isola Group. All rights reserved.