

**IPC-4101 /21 UL - File Number E41625**

DE104 offers excellent thermal resistance, due to its special resin system and a low coefficient of thermal expansion in the Z-axis.

### PRODUCT FEATURES

#### Industry Recognition

- UL File Number: E41625
- RoHS Compliant

#### Processing Advantages

- FR-4 process compatible
- UV blocking and AOI fluorescence

### PRODUCT AVAILABILITY

#### Standard Material Offering: Laminate

- 2 to 93 mil (0.05 to 2.4 mm)

#### Copper Foil Type

- HTE Grade 3

#### Copper Weight

- ½, 1 and 2 oz (18, 35 and 70 µm) available
- Thinner copper foil available

#### Standard Material Offering: Prepreg

- Roll or panel form
- Tooling of prepreg panels

#### Glass Fabric Availability

- E-glass
- Square weave glass
- Mechanically spread glass

The glass transition temperature (Tg) is 135°C (DSC). Time to delamination of the laminate at a temperature of 260°C is 12 minutes and the decomposition temperature (Td) is 315°C. The product is listed as FR-4 and can be processed using standard parameters. DE104 multilayer (ML) corresponds to NEMA-grade FR-4 and meets the requirements of IPC-4101.

### PRODUCT ATTRIBUTES



### TYPICAL MARKET APPLICATIONS



### ORDERING INFORMATION:

Contact your local sales representative or contact [info@isola-group.com](mailto:info@isola-group.com) for further information.

#### Isola Group

6565 West Frye Road Chandler, AZ 85226  
Phone: 480-893-6527  
Fax: 480-893-1409

#### Isola Asia Pacific

(Hong Kong) Ltd. 12/F, Kin Sang Commercial Centre, 49 King Yip Street, Kwun Tong, Kowloon,  
Hong Kong  
Phone: 852-2418-1318  
Fax: 852-2418-1533

#### Isola GmbH

Isola Strasse 2 D-52348 Düren, Germany  
Phone: 49-2421-8080  
Fax: 49-2421-808164

# Typical Values Table

Property		Typical Value	Units		
			Metric (English)	Test Method	
				IPC-TM-650 (or as noted)	
Glass Transition Temperature (Tg) by DSC		135	°C	2.4.25C	
Decomposition Temperature (Td) by TGA @ 5% weight loss		315	°C	2.4.24.6	
Time to Delaminate by TMA (Copper removed)	T260	12	Minutes	2.4.24.1	
Z-Axis CTE	A. Pre-Tg B. Post-Tg C. 50 to 260°C, (Total Expansion)	70 250 4.2	ppm/°C ppm/°C %	2.4.24C	
X/Y-Axis CTE	Pre-Tg	16/13	ppm/°C	2.4.24C	
Thermal Conductivity		0.36	W/m·K	ASTM E1952	
Thermal Stress 10 sec @ 288°C (550.4°F)	A. Unetched B. Etched	Pass	Pass Visual	2.4.13.1	
Dk, Permittivity	A. @ 100 MHz B. @ 500 MHz C. @ 1 GHz D. @ 2 GHz E. @ 5 GHz	4.46 4.40 4.37 4.35 4.32	—	2.5.5.3 2.5.5.3 2.5.5.9 2.5.5.5 2.5.5.5	
Df, Loss Tangent	A. @ 100 MHz B. @ 500 MHz C. @ 1 GHz D. @ 2 GHz E. @ 5 GHz	0.020 0.021 0.022 0.023 0.024	—	2.5.5.3 2.5.5.3 2.5.5.9 2.5.5.5 2.5.5.5	
Volume Resistivity	A. C-96/35/90 B. After moisture resistance C. At elevated temperature	— $1.3 \times 10^6$ $3.4 \times 10^7$	MΩ·cm	2.5.17.1	
Surface Resistivity	A. C-96/35/90 B. After moisture resistance C. At elevated temperature	— $1.0 \times 10^6$ $7.2 \times 10^6$	MΩ	2.5.17.1	
Dielectric Breakdown		>50	kV	2.5.6B	
Arc Resistance		105	Seconds	2.5.1B	
Electric Strength (Laminate & laminated prepreg)		54 (1350)	kV/mm (V/mil)	2.5.6.2A	
Comparative Tracking Index (CTI)		2	Class (Volts)	UL 746A ASTM D3638	
Peel Strength	A. B. Standard profile copper 1. After thermal stress 2. At 125°C (257°F) 3. After process solutions	1.23 (7.0) 1.58 (9.0) 1.23 (7.0) 1.58 (9.0)	N/mm (lb/inch)	2.4.8C 2.4.8.2A 2.4.8.3 2.4.8.3	
Flexural Strength	A. Length direction B. Cross direction	579 (84.0) 450 (65.2)	MPa (kpsi)	2.4.4B	
Tensile Strength	A. Length direction B. Cross direction	393 (57.0) 292 (42.4)	MPa (kpsi)	ASTM D3039	
Moisture Absorption		0.3	%	2.6.2.1A	
Flammability (Laminate & laminated prepreg)		V-0	Rating	UL 94	
Relative Thermal Index (RTI)		130	°C	UL 94	

## NOTES

Visit our site <http://www.isola-group.com> for more details.

Revisions:

A: Initial release - 4/17

B; Correct 5GHz Df label - 8-17

C: Corrected units for Flexural and Tensile Strength - 8/18

D: Change MOT to RTI 5/19

Isola, the Isola logo, Astra, Chronon, GETEK, I-Fill, IsoDesign, IsoStack, I-Speed, I-Tera, Polyclad, Stratus, TerraGreen, and The Base for Innovation are registered trademarks or trademarks of ISOLA USA Corp. in the United States and in other countries. Copyright © 2021 Isola Group. All rights reserved.